

# **BLANK PAGE**



# Indian Standard

# SPECIFICATION FOR HANDLOOM COTTON ANGAVASTRAM

UDC 677:21:064



# © Copyright 1974

INDIAN STANDARDS INSTITUTION MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG NEW DELHI 110001

# AMENDMENT NO. 1 APRIL 1978

# IS: 7216 - 1974 SPECIFICATION FOR HANDLOOM COTTON ANGAV ASTRAM

#### Alterations

(Page 4, Table 1, col 4 and 5, against 'Tolerance') — Substitute '± 5 percent' for '± 5' at both the places.

(Page 4, Table 2)

- a) Col 4, against Sl No. (ii) Substitute '1S: 1383 1977+ (Mild method)' for 'IS: 1383 1960†'.
- b) Foot-note with 't' mark Substitute the following for the existing matter:

'tMethod of determination of scouring loss in grey and finished cotton textile materials (first revision).'

(TDC 13)

Printed at Simco Printing Press, Delhi, India

# AMENDMENT NO. 1 APRIL 1978

# IS: 7216 - 1974 SPECIFICATION FOR HANDLOOM COTTON ANGAV ASTRAM

### Alterations

(Page 4, Table 1, col 4 and 5, against 'Tolerance') — Substitute '± 5 percent' for '± 5' at both the places.

(Page 4, Table 2)

- a) Col 4, against Sl No. (ii) Substitute 'IS: 1383 1977† (Mild method)' for 'IS: 1383 1960†'.
- b) Foot-note with 't' mark Substitute the following for the existing matter:

'tMethod of determination of scouring loss in grey and finished cotton textile materials (first revision).'

(TDC 13)

Printed at Simco Printing Press, Delhi, India

# Indian Standard

# SPECIFICATION FOR HANDLOOM COTTON ANGAVASTRAM

# Handloom and Khadi Sectional Committee, TDC 13

Chairman

Representing

DIRECTOR OF HANDLOOMS
TEXTILES

Directorate of Handlooms & Textiles, Government of Tamil Nadu, Madras

Members

JOINT DIRECTOR OF HANDLOOMS AND TENTILES (Alternate to Director of Handlooms and Textiles)

SHRI B. P. AGARWAL

SHRI C. SINGH ( Alternate)

Business Manager

BUSINESS MANAGER

CHIEF EXECUTIVE OFFICER

DEPLTY EXECUTIVE OFFICER
(DEVELOPMENT) (Alternate)
CHIEF INSPECTING OFFICER
DEPUTY CHIEF INSPECTING
OFFICER (Alternate)
SHEI PARITOSH DAS

SHRI P. K. DAS (Alternate) SHRI D. S. V. IYER SHRI S. P. KUMARIA

SHRI MOHINDER SINGH (Alternate)
SHRI K. MANIVANNAN
D

SHRI C. R. YADAV ( Alternate ) SHRI R. K. MEHRA SHRI P. B. MEHTA ( Alternate )

SHRI MANUBHAI MEHTA

Government of Uttar Pradesh, Lucknow

The Andhra Handloom Weavers' Co-operative Society Ltd, Vijayawada

The Tamil Nadu (Madras State) Handloom Weavers' Co-operative Society Ltd, Madras Maharashtra State Khadi & Village Industries Board, Bombay

Textiles Committee, Bombay

Directorate of Industries, Government of West Bengal, Calcutta

All India Handloom Board, Bombay Directorate of Industries, Government of Punjab, Chandigarh

Directorate of Industries, Government of Haryana, Chandigarh

Ministry of Defence (DGI)

Gujarat Rajya Khadi Gramodyog Board, Ahmedabad

(Continued on page 2)

# © Copyright 1974 INDIAN STANDARDS INSTITUTION

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

## IS: 7216 - 1974

(Continued from page 1)

Members

Representing Ministry of Defence (R & D)

All India Handloom Board, Bombay

SHRI P. S. NADKARNI

SHRI M. R. RAO (Alternate)

PRINCIPAL, INDIAN INSTITUTE OF

HANDLOOM TECHNOLOGY, Varanasi

SHRI H. RAMAKRISHNA RAO

All India Handloom Fabrics Marketing Co-

SHRI K. S. GOPALA RAO ( Alternate ) SHRI B. P. SENGUPTA

SHRI A. T. BASAK ( Alternate ) SHRI SOMDUTE VIDYALANKAR SHRI D. V. LELE ( Alternate )

SHRI S. M. CHARRABORTY, Director ( Tex )

operative Society Ltd, Bombay

Inspection Wing, Directorate General of Supplies & Disposals, New Delhi

Khadi & Village Industries Commission, Bombay

Director General, ISI (Ex-officio Member)

Secretary

SHRI P VENKATARAMAN Deputy Director (Tex), ISI

# Handloom and Khadi Cotton Cloth Subcommittee, TDC 13:1

Convener

PRINCIPAL, INDIAN INSTITUTE OF All India Handloom Board, Bombay HANDLOOM TECHNOLOGY, Varanasi

Members

SHRI B. P. AGARWAL

Government of Uttar Pradesh, Lucknow

SHRI C. SINGH ( Alternate ) SHRI M. S. GOKHALE

Khadi & Village Industries Commission, Bombay

SHRI S. RAMASWAMY ( Alternate ) SHRI N. V. GOVINDAYYA

The Handicrafts and Handlooms Exports Corporation of India Ltd, Madras

SHRI B. N. GUPTA

Messrs Guptajee, New Delhi

SHRI A. R. R. DESHPANDE ( Alternate )

SHRI B. R. KOWSHIK

Textiles Committee, Bombay

SHRI S. P. KUMARIA

Directorate of Industries, Government of Puniab. Chandigarh

SHRI MOHINDER SINGH ( Alternate )

SHRI R. K. MEHRA

Ministry of Defence

SHRI P. B. MEHTA ( Alternate ) SHRI N. C. NATABAJAN

Kerala State Handloom Weavers' Co-operative Society Ltd, Trivandrum

SHRI R. VIJAYAPPAN NAIR ( Alternate )

PRINCIPAL, INDIAN INSTITUTE OF HANDLOOM TECHNOLOGY, SALEM

SHRI B. P. SENGUPTA

All India Handloom Board, Bombay

Inspection Wing, Directorate General of Supplies & Disposals, New Delhi

SHRI A. T. BASAK ( Alternate )

SPECIAL OFFICER

The Tamil Nadu (Madras State) Handloom Weavers' Co-operative Society Ltd, Madras

TEXTILE OFFICER ( Alternate )

# Indian Standard

# SPECIFICATION FOR HANDLOOM COTTON ANGAVASTRAM

# 0. FOREWORD

- 0.1 This Indian Standard was adopted by the Indian Standards Institution on 18 February 1974, after the draft finalized by the Handloom & Khadi Sectional Committee had been approved by the Textile Division Council.
- **0.2** The ANGAVASTRAMS, also known as DUPATTAS, are commonly used as an important part of dress in the southern states. The standard has been prepared with a view to assist the handloom weavers in producing ANGAVASTRAMS of right quality.
- 0.3 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS: 2-1960\*. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

### 1. SCOPE

- 1.1 This standard prescribes the constructional particulars and other requirements of handloom cotton ANGAVASTRAMS.
- 1.2 This standard does not specify the general appearance, feel, finish, etc, of the fabric.

### 2. MANUFACTURE

2.1 Constructional Particulars — Constructional particulars shall conform to those given in Table 1. The yarn used shall conform to IS: 171-1973†.

# 3. REQUIREMENTS

3.1 The requirements of fabric shall conform to those given in Table 2.

<sup>\*</sup>Rules for rounding off numerical values (revised).
†Specification for grey cotton yarn (second revision).

# TABLE 1 CONSTRUCTIONAL PARTICULARS OF HANDLOOM COTTON ANGAVASTRAM

( Clause 2.1 )

VARIETY No.	APPROXIMATE C	OUNT OF YARN	Enns/dr	n Picks/dm	
No.	Warp	Weft	`		
(1)	(2)	(3)	(4)	(5)	
1	80s (or 7.3 tex)	80s (or 7.3 tex)	324	332	
2	80s (or 7.3 tex)	80s (or 7.3 tex)	316	308	
3	100s (or 5.9 tex)	100s (or 5.9 tex)	362	354	
TOLERANCE	± 5 percent	± 5 percent	± 5	± 5	
METHOD OF TEST	IS: 1315-1959*	IS: 1315-1959*	IS: 1963-1969†	IS: 1963-1969†	

<sup>\*</sup>Method for determination of universal count of cotton varn.

<sup>†</sup>Methods for determination of threads per decimetre in woven fabrics (first revision).

TABLE 2	REQUIREMENTS OF HANDLOOM COTTON ANGAVASTRAN	ı
	(Clause 3 1)	

	( Chuns	31)	
Sr No.	CHARACTERISTIC	REQUIREMENT	METHOD OF TEST
(1)	(2)	(3)	(4)
i)	Dimensional changes, percent, Max:		IS:2977-1964*
	Grey	4	
	Bleached	2	
ii)	Scouring loss, percent, Max:		IS: 1383-1960†
	Grey	10	
	Bleached	<b>2·</b> 5	
iii)	Length	As agreed,	IS: 1954-1969‡
iv)	Width	As agreed	IS: 1954-1969‡
		-2 percent	

Note — The usual lengths are 1.2, 1.3, 1.8, 2.1 or 2.7 m.

Methods for determination of length and width of fabrics (first revision).

# 4. INSPECTION

- 4.1 The cloth when visually inspected should be reasonably free from:
  - a) west crack of more than 2 missing picks across the width of the material;

<sup>\*</sup>Method for determination of dimensional changes of woven fabrics (other than wool) on soaking in water.

<sup>†</sup>Method for determination of scouring loss in grey and finished cotton textile materials.

- b) prominently noticeable weft bar due to the difference in raw material, count, twist, lustre, colour, shade or pick spacing of adjacent groups of weft yarn;
- c) more than two adjacent ends running parallel, broken or missing and extending beyond 15 cm;
- d) prominent selvedge defect;
- e) noticeable warp or west float in the body of the material;
- f) noticeable oil or other stain in the material;
- g) noticeable hole, cut or tear up to 3 mm in size in the body of the fabric; and
- h) smash definitely rupturing the texture of the materials.
- 4.1.1 Above are some of the common defects. For details of these defects a reference may be made to IS: 4125-1967\*.

## 5. MARKING

- 5.1 Each piece shall be marked or labelled with the following information:
  - a) Name of the material;
  - b) Manufacturer's name, initials or trade-mark;
  - c) Length and width of piece; and
  - d) Count of warp and weft yarn.
  - 5.1.1 The fabric may also be marked with the ISI Certification Mark.

NOTE — The use of the ISI Certification Mark is governed by the provisions of the Indian Standards Institution (Certification Marks) Act and the Rules and Regulations made thereunder. The ISI Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well-defined system of inspection, testing and quality control which is devised and supervised by ISI and operated by the producer. ISI marked products are also continuously checked by ISI for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of the ISI Certification Mark may be granted to manufacturers or processors, may be obtained from the Indian Standards Institution.

#### 6. PACKING

6.1 Unless otherwise agreed upon by the buyer and the seller the fabrics shall preferably be packed in bales or cases in conformity with the procedure laid down either in IS: 1347-1959† or IS: 293-1967‡ if not stipulated by the buyer.

<sup>\*</sup>Glossary of terms pertaining to defects in fabrics.

tCode for inland packaging of cotton cloth and yarn.

Seaworthy packaging of cotton cloth and yarn (second revision).

### INDIAN STANDARDS

#### ON

#### HANDLOOM COTTON FABRICS

```
IS:
           Handloom cotton bed sheets, grey, bleached, dyed or striped
 745-1955
 749-1955
           Handloom cotton dungri cloth, grey
           Handloom cotton lungies, striped or checked
 750-1956
 752-1955
           Handloom cotton muslin, bleached
 753-1955
           Handloom cotton pugri cloth, bleached or dyed
 755-1955
           Handloom cotton malmal, bleached
 756-1955
           Handloom cotton dosuti, grey, scoured, bleached or dyed
 757-1971
           Handloom cotton lint, absorbent, bleached (first revision)
 758-1969
           Handloom cotton gauze, absorbent (revised)
 854-1956
           Handloom cotton turkish towels, bleached, striped, checked or dyed
 855-1966
           Handloom cotton honeycomb towels, bleached, striped, checked or dyed
 856-1971
           Handloom cotton huckaback towels (first revision)
 857-1956
           Handloom cotton napkins, bleached, striped, checked or dyed
 858-1969
           Handloom cotton table cloth, bleached, striped, checked or dyed
 859-1956
           Handloom cotton dusters, grey, striped and checked
 860-1956
           Handloom cotton sponge cloth, grey, striped and checked
 861-1956
           Handloom cotton jaconet cloth, grey, dressed
 862-1956
           Handloom cotton ticking cloth, grey, striped
 863-1969
           Handloom cotton bandage cloth (revised)
 864-1956
           Handloom cotton light sheeting, grey
1093-1957
           Handloom cotton Madras handkerchiefs
1094-1957
           Handloom cotton gada cloth, grey
1095-1957
           Handloom cotton dress materials, bleached, dyed, printed, striped or checked
1096-1957
           Handloom cotton Holland cloth, unscoured
           Handloom cotton mosquito netting, bleached or dyed
1097-1957
1098-1957
            Handloom cotton cambric, bleached
1099-1957
            Handloom cotton lining cloth, dyed
1100-1957
           Handloom cotton crepe, bleached or dyed
1101-1957
            Handloom cotton cellular shirting, bleached or dyed
           Handloom buckram cloth ( revised)
Handloom cotton mainsook, bleached or dyed
1102-1963
1240-1958
1241-1958
           Handloom cotton calico, bleached or dyed
1242-1958
           Handloom cotton shirting, bleached, dyed, striped, checked or printed
1243-1958
            Handloom cotton coating, bleached, dyed, striped or checked
1244-1958
            Handloom cotton longcloth, bleached or dyed
           Handloom cotton pyjama cloth, grey, with stripes
1245-1958
1246-1958
           Handloom cotton curtain cloth, bleached, dyed, striped, checked or printed
1247-1958
           Handloom cotton Madras check
1451-1959
           Handloom cotton drills, bleached or dyed
1556-1960
           Handloom cotton poplin, bleached or dyed
            Handloom cotton twills, bleached or dyed
1579-1960
1814-1961
            Handloom cotton MOOTUS, striped or checked
1937-1961
            Handloom cotton bleeding Madras
1939-1961
            Handloom cotton handkerchiefs, bleached, striped or checked
2158-1962
           Handloom viscose staple fibre shirting, bleached, dyed, striped or checked
2159-1962
            Handloom viscose staple fibre shirting, bleached, dyed, striped or checked
2160-1962
            Handloom viscose staple fibre coating, bleached, dyed, striped or checked
2172-1962
            Handloom filament rayon saris
2715-1964
            Handloom cloth, collar, white
6237-1971
            Handloom cotton cloth for plaster of Paris bandages and cut bandages
6906-1973 Requirements for colour fastness of handloom cotton textiles
```

# PUBLICATIONS OF INDIAN STANDARDS INSTITUTION

## INDIAN STANDARDS

Over 7 500 Indian Standards covering various subjects have been issued so far. Of these, the standards belonging to the Textile Group fall under the following categories:

Aeronautical textiles Chemical test methods Colour fastness of textile materials Cotton fabrics - handloom, khadi, and mill-made Dyestuffs Grading of fibres and varns Grading of raw silk Hosierv Jute - bags and fabrics Jute mill accessories Narrow fabrics National flag of India Nylon fabrics Packaging codes Physical test methods Rayon fabrics

Telephone: 27 01 31 (20 lines)

Rayon fabrics, handloom Ropes and cordages Sampling of textiles, methods for Silk fabrics - handloom and khadi Sizing and finishing materials Spinning machinery components Terminology Textile floor coverings Textile materials for fishing Textile mill accessories (other than jute mills) Twines Weaving machinery components Wool fabrics - handloom, khadi. and mill-made Yarn and similar structures Unclassified

# OTHER PUBLICATIONS

ISI Bulletin ( Published Ex	ery Monti	h )					
Single Copy	•••	•••	•••	•••	•••	Rs	3.00
Annual Subscription	•••	•••	•••	•••	•••	Rs	<b>25</b> ·00
Standards: Monthly Additi	ons						
Single Copy						Re	0.30
Annual Subscription						Rs	3.00
Annual Reports ( from 194	8-49 Onw	ards )		•••	Rs 2	00 to	5.00
ISI Handbook, 1972	•••	•••		•••	•••	Rs	<b>20</b> ·00

### INDIAN STANDARDS INSTITUTION

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110001

, , ,	
Branch Offices:	Telephone
'Sadhna', Nurmohamed Shaikh Marg, Khanpur, AH	MEDABAD 380001 2 03 91
F Block, Unity Bldg, Narasimharaja Square, BANG.	ALORE 560002 2 76 49
534 Sardar Vallabhbhai Patel Road, BOMBAY 4000	07 35 69 44
5 Chowringhee Approach, CALCUTTA 700013	23-08 02
Flat No. 1030-31 (First Floor), Sector 22B, CHANDIC	SARH 160022 2 83 20
5-8-56,57 Nampally Station Road, HYDERABAD 50	00001 4 57 11
117/418 B Sarvodaya Nagar, KANPUR 208005	82 72
54 General Patters Road, MADRAS 600002	8 3 7 8 1
B. C. I. Bldg (Third Floor), Gandhi Maidan East, P	ATNA 800004 2 56 55

Printed at New India Printing Press Khuria, India

Telegrams: Manaksanstha